TECHNICAL PRODUCT DATA SHEET

solidian.

solidian ANTICRACK Q95-CCE-38 (F01R01)

Symmetrical, bidirectional reinforcement mesh (type Q) made of media-resistant carbon fiber reinforced polymer (CFRP) with sanded surface for the reinforcement of concrete components

Material						
Fiber material	C (Carbon)					
Impregnation material	E (Epoxy resin)					
Color	black					
Surface finish	rough (sanded)					
Chemical resistance of the reinforcement in relation to the exposure classes in accordance with EN 206	XD3	Chlorides, except seawater				
	XS3	Chlorides from seawater				
	ХАЗ	Chemical attack				

Geo	metry and structure		Unit	Value	Standard
		longitudinal	[0]	0	
	Directions of the fiber strands	transversal	- []	90	
		longitudinal	F 7	5,7	
φh	Mean value of fiber strand width	transversal	– [mm] —	6,2	
		longitudinal	[]	4,5	
Φv	Mean value of fiber strand height	transversal	– [mm] –	4,5	
		longitudinal	[]	3,35	
 ¶nm	Nominal diameter	transversal	– [mm] –	3,35	
^	Naminal managementional area and fiber stress d	longitudinal	[2]	8,8	10 10 10 1
A _{nm}	Nominal cross-sectional area per liber strand	transversal 8,8	150 10406-1		
		longitudinal	[2/]	232	
anm	Nominal cross-sectional area per meter	transversal [mm²/m] 232 -	_		
	Fileer mees continued over ear fileer streed	longitudinal	[2]	3,62	
A _{f,nm}	Fiber cross-sectional area per liber strand	oss-sectional area per fiber strand [mm ²] - transversal		3,62	
		longitudinal	[2/]	95	
d f,nm	Fiber cross-sectional area per meter	transversal	- [mm-/m]	95	
	Marchan Adda	longitudinal	[]	38	
S	Mesh width	transversal	38		
6	Clear spacing of the fiber strends	longitudinal		32,8	
51	Clear spacing of the liber strands	transversal		33,5	
hg	Mesh height (average value of the maximum height)		[mm]	6,7	-
g	Weight per unit area of the non-metallic reinforcement		[g/m²]	929	-
Кü	Degree of coverage of the mesh		[%]	30,0	-
r _{min}	Minimum permissible radius of curvature		[mm]	400	_

TECHNICAL PRODUCT DATA SHEET

solidian.

Mate	erial properties		Unit	Value	Standard
С	Bulk density of the fiber composite material		[g/cm ³]	1,45	ISO 1183-1
Х	Coefficient of thermal expansion	along the fiber	[10 ⁻⁶ 1/K]	0,5	-
Г _{д0}	Glass transition temperature (DMA)		[°C]	≥ 110	DIN 65583
	Recommended operating temperature range		[°C]	-20 to +80	-
	Building material class components ¹⁾		[-]	A2, non-combustible	DIN 4102-1
	Building material class reinforcement mesh		[-]	E, normally flammable	EN 13501-1
Mecl	hanical properties		Unit	Value	Standard
f _{nm,k}	Characteristic short-term tensile strength related to the nominal cross-sectional area	longitudinal	- [MPa]	1200	ISO 10406-1
		transversal		1200	
Enm	Young's modulus related to the nominal cross-sec- tion	longitudinal	- [MPa]	100000	ISO 10406-1
		transversal		100000	
	Mean short-time tensile strength related to the	longitudinal		≥ 3910	ISO 10406-1
nm,m	fiber cross-sectional area	transversal	[MPa]	≥ 3910	
	Characteristic short-term tensile strength	longitudinal	[MPa]	≥ 2917	ISO 10406-1
nm,k	related to the fiber cross-sectional area	transversal		≥ 2917	
E _{f,nm,m}	Mean Young's modulus related to the fiber cross-sectional area	longitudinal	[MPa]	≥ 243000	ISO 10406-1
		transversal		≥ 243000	
	Characteristic elongation at failure under tensile	longitudinal	[‰]	≥ 12,0	ISO 10406-1
nm,uk	load of the non-metallic reinforcement	transversal		≥ 12,0	
F _{nm,k}	Characteristic tensile force transmission of the non- metallic reinforcement per m width	longitudinal	- [kN/m]	278	ISO 10406-1
		transversal		278	
urti	her key values		Unit	Value	Standard
g	Recommended maximum grain size in concrete ²⁾		[mm]	8	-
tan	dard goods variety		Unit	Value	Tolerance
Single mesh —		Length	- [m]	6,0	± 16 mm
		Width		2,30	± 12 mm
Roll in CARGO SYSTEM -		Length	- [m]	≤ 130,0	-
		Width		2,30	± 12 mm
Roll –		Length	- [m]	≤ 250,0	-
		Width		3,0	± 12 mm

The CARGO SYSTEM is a stacking and transport rack with unrolling device for our reinforcement mesh.

Transport and storage

Non-metallic reinforcements from solidian GmbH must not be damaged during transportation, storage, processing and installation and must not be exposed to temperatures higher than 80°C. They must be stored dry, protected from the weather and without touching the ground. They must be protected from UV radiation and moisture until concreting and be free from bond-reducing impurities (e.g. grease, soil, loose concrete residues).

¹⁾ Building material class for components from a component thickness of 30 mm with a minimum concrete cover of 14 mm or for components with a component thickness of 30 mm and a single layer of centrally arranged reinforcement mesh.

²⁾ $d_g = 16$ mm possible depending on the manufacturing process.

TECHNICAL PRODUCT DATA SHEET

solidian.

Measurement

Specified values were determined on the product itself. Deviating properties may occur in the structural component or during processing. We recommend checking the values by suitable structural component tests with the concrete formulation used in each case.

Tests

As part of our in-house production control, two test units with 6 tensile tests each per reinforcement direction are carried out for each production order for quality assurance purposes, from which the characteristic short-term tensile strength is determined. All other measured values are determined as part of a comprehensive product gualification and are not subject to continuous control.

The described tensile tests per production order are included in the sales price. If you need an extended production control for your construction project, please contact us. We will be happy to provide you with a non-binding quotation for additional production-related tests.

Country-specific regulations

For the use of the product, the respective national regulations at the place of use apply, in Germany for example the building regulations of the federal states, and the technical provisions based on these regulations.

The design is generally carried out in accordance with the applicable standards for reinforced concrete components, whereby adjustments must be made for fiber composite reinforcements if applicable standards, guidelines (e.g. guideline for Germany "Concrete components with non-metallic reinforcement" of the German Committee for Reinforced Concrete (DAfStb) and the co-applicable standards cited in the guideline) etc. do not exist for reinforcements made of fiber reinforced polymer materials. Accordingly, the respective national standards and regulations must be taken into account in the design.

Processing information

All work must only be carried out by trained personnel. Damaged fiber bundles (resin spalling, brittle areas, etc.) must not be installed, as the specified load-bearing capacity cannot be guaranteed. The specified values of the product only apply when used as intended.

For further information, please refer to the current Technical Information for our solidian reinforcement products.

Ecology and health protection

REGULATION (EC) NO. 1907/2006 - REACH.

This product is an article as defined in Article 3 of Regulation (EC) No 1907/2006 (REACH). It does not contain substances that are released from the article during normal use. A safety data sheet according to Article 31 of the same regulation is not required to place this product on the market, to transport it or to use it. For safe use, follow the instructions from this data sheet. To our current knowledge, this product does not contain any SVHC (Substances of Very High Concern) according to Annex XIV of the REACH Regulation or substances published on the Candidate List by the European Chemicals Agency at concentrations above 0,1% (w/w).

Industrial safety and health

The currently valid legal regulations on occupational health and safety must be observed during all transportation activities. Protective measures, such as wearing cut-resistant gloves, safety goggles and a dust mask, must be observed when working with cutting equipment. The specific handling of fiber reinforced polymers should be based on the respective national technical regulations.

Legal information

The above information is based on our knowledge and experience under normal circumstances, provided that the product has been transported, stored and used or processed properly and in accordance with the information in this product data sheet and the Technical Information for our solidian reinforcement products. The work results that can be achieved with our products depend in particular on their use and processing. The suitability of the product for the specific application must be checked in advance on your own responsibility.

Since non-metallic reinforcements are not yet regulated by building authorities in most countries, planners, specialist planners, building authorities, structural engineers, experts, etc. must be consulted for load-bearing components and countryspecific regulations must be observed.

We reserve the right to make changes to the product specifications. Third-party property rights must be observed. In all other respects, our respective terms and conditions of sale and delivery apply. The latest technical product data sheet at the time of purchase of our products shall apply.

Date: 21.06.2024 Version: 2406 solidian ANTICRACK Q95-CCE-38 Technical Product Data Sheet v2406.docx

Page 3 of 3



Sigmaringer Straße 150 72458 Albstadt Germany 🔮 +49 7431 103135 info@solidian.com

P. Slavka Rozgaja 3 47000 Karlovac Croatia

+385 47 693300





